


DuPont™ Tyvek®


2524B



Application:

Flexible sheets for water proofing – Part 2: Underlays for walls

EN 13859-2 (Dec 2004)
walls with open joints (1)



Application:

Flexible sheets for water proofing – Part 1: Underlays for discontinuous roofing

EN 13859-1 (Feb 2005)



Style name: **2524B**
Type of carrier: **laminate HD-PE & PP**

Language: **English**
Applicable for: **All regions**

PROPERTY	METHOD	UNITS	NOMINAL (Mean value)	TOLERANCE	
				Minimum	Maximum
Length (expressed in m)	EN 1848-2	%	Customer related	0	-
Width (expressed in mm)	EN 1848-2	%	Customer related	-0,5	+1,5
Straightness	EN 1848-2	mm	-	-	30
Mass per unit area	EN 1849-2	gr/m ²	195	180	210
Reaction to fire (EN 13501-1)	EN 11925-2	Class	E	-	
Water tightness	EN 1928 (method A)	Class	W1	-	-
Water vapour transmission (s _d)	EN ISO 12572	m	0,035	0,02	0,05
Maximum tensile force (MD)	EN 12311-1	N/50mm	410	340	480
Elongation at max. tensile force (MD)	EN 12311-1	%	14	9	19
Maximum tensile force (XD)	EN 12311-1	N/50mm	335	260	400
Elongation at max. tensile force (XD)	EN 12311-1	%	19	13	25
Resistance to tearing MD (nail shank)	EN 12310-1	N	300	200	400
Resistance to tearing XD (nail shank)	EN 12310-1	N	340	220	460
Resistance to penetration of air	EN 12114	m ³ /(m ² hr 50Pa)	-	-	0,1
Dimensionnel stability (MD & XD)	EN 1107-2	%	-	-	1
Flexibility at low temperature	EN 1109	°C	-	-	-40
Artificial ageing by UV and heat (1)	EN 1297 & EN 1296	Residual value	aged/new material	-	-
Maximum tensile force in MD	EN 12311-1	%	90	-	-
MD elongation at max tensile force	EN 12311-1	%	80	-	-
Maximum tensile force in XD	EN 12311-1	%	90	-	-
XD elongation at max tensile force	EN 12311-1	%	80	-	-
Water tightness	EN 1928 (A)	Class	W1	-	-
ADDITIONAL PROPERTIES					
Product-/Functional layer thickness	-	mm	0,6 / 0,220	-	-
Temperature resistance	-	°C	-	-40	+100
Water column	EN 20811	m	-	2	-
Windtight	-	-	yes	-	-
Reaction to fire (2)	EN 13501-1	Class	D-s1, d2	-	-
Max width of joints (vertical & horizontal)	-	cm	-	-	3
Min width of façade elements	-	-	-	-	2 x joint width
Full UV exposure (as standard underlay)	-	months	-	-	6
Full UV exposure (for walls with open joints before installation of façade elements)	-	months	0,5	-	4

(1) according to EN13859-2: for walls with open joints, artificial aging by UV is 5000 hrs (standard wall/roof application is 336hrs),
(2) when the product is installed on mineralwool, the reaction to fire class D-s1, d2 is achieved (KB-Hoch-080796)

DuPont de Nemours (Luxembourg) S.à.r.l.
L-2984 Luxembourg
Tyvek® Marketing
Fax: +352 3666 5021
Tyvek® Customer Service
Fax +352 3666 5018
Tyvek® Manufacturing
Fax +352 3666 5020
E-mail: tyvek.info@lux.dupont.com

Some test methods are modified according to the EN 13859-1&-2 and/or according to the DuPont DIN EN ISO 9001 (2000) certified quality system (for details please contact your regional DuPont representative). This information corresponds to our current knowledge on the subject. It is offered in accordance with Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of the Member States relating to construction products ("European Construction Products Directive"). It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.

Effective date:

22.10.2008

www.construction.tyvek.com

Copyright © 2008 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™ & Tyvek® are registered trademarks or trademarks of E.I. DuPont de Nemours and Company or its affiliates

Tyvek.

